
ERAMOSA Linear cut

LIMESTONE



AVAILABLE FINISHES Polished Antique	Smooth Honed	Sandblasted
APPLICATIONS Exterior Interior	Horizontal Vertical	Commercial Residential

PHYSICAL TEST RESULTS

		Imperial	Metric
Absorption by weight	ASTM C97	0.08%	0.08%
Density	ASTM C97	172 lb/ft³	2 777 kg/m ³
Compressive strength	ASTM C170	43 750 Psi	301.7 MPa
Flexural strength	ASTM C880	N/A	N/A
Modulus of rupture	ASTM C99	4 860 Psi	33.5 MPa





QUARRY OWNERS | BLOCKS | SLABS | TILES | LANDSCAPING PRODUCTS | CURBS

polycor.com

QUARRY LOCATION: Wiarton, ON, Canada

Computer generated images and printed reproductions may not accurately match natural stone colors.